

## **BITUCOAT BF-Tape**

### **Properties:**

*BITUCOAT BF-Tape* is a malleable, temperature-resistant bitumen strip that is used for strengthening construction and movements joints (loop forming).

*BITUCOAT BF-Tape* adheres strongly to all *BITUCOAT* products and is to a large extent resistant to diluted acids and bases.

*BITUCOAT BF-Tape* must not be allowed to interact with solvents, such as those present in some solvent-containing bitumen products, as this would lessen its adhesive properties.

### **Technical data:**

Storage	:	6 months if stored frost-free, cool and upright in its original packaging
Width	:	25 cm
Thickness	:	approx. 1 mm
Packaging	:	10-m rolls
Colour	:	dark grey
Processing temperature	:	0°C to +50°C
Drip point	:	> 100°C
Weight	:	approx. 1000 g/m <sup>2</sup>
Tear resistance	:	> 70 N/ 10 mm
Consumption	:	depending on application, approx. 5 mm overlap

### **Processing:**

All subsurfaces must be solid and stable, clean and free of oil or grease as well as free of flaws, gaping cracks and flashes. *BITUCOAT* ground must be applied to the respective area as an adhesive agent.

The appropriate *BITUCOAT* thick layer is applied to both sides of the joint where surfaces have been prepared as explained above, and the *BITUCOAT BF-Tape* is then put into this. Whereby the edges of the strip must be embedded in the film.

The *BITUCOAT BF-Tape* can be laid smoothly over joints that move only slightly. In the case of movement joints, the strip must be laid in loops, whereby a round cord, e.g. out of closed cellular foam or SBR, must be inserted into the joint.

**Please note that all joints sealed with *BITUCOAT BF-Tape* must be protected against any mechanical damage.**

Proper and as a result successful use of our products is beyond our control. For this reason we can only guarantee the quality of our products within the framework of our Terms and Conditions of Sale and Delivery, not, however, for their successful processing. All data and information in these instructions are based on the latest state-of-the-art technology, we expressly reserve the right to make modifications or adaptations to the development. The consumption data quoted by us can only be average experience values, deviations in individual cases are possible and can therefore not be excluded.

TPH 110808