

FIX-O-FLEX Primer

Properties:

FIX-O-FLEX Primer is a solvent-containing adhesive agent on a polyurethane basis that should be applied before processing *FIX-O-FLEX* adhesive and sealing compounds on absorbent subsurfaces such as concrete, clinker, porous concrete, cement asbestos, plaster and natural stone (marble, granite etc.).

The application of *FIX-O-FLEX Primer* is prescribed for jointing with *FIX-O-FLEX H* in compliance with DIN 18540-F.

Technical data:

Storage	:	cool and dry between 5° and 25°C, 9 months in closed original containers
Consistency	:	fluid
Colour	:	yellowish transparent
Odour	:	characteristic
Spec. Density	:	approx. 0.9 g/cm ³
Flash off time	:	approx. 1 h to max. 6 h
Processing temperature	:	+5° to +30°C (temperature of structural component)
Delivery form	:	500 ml tin can

Processing:

The subsurface must be dry, hard, stable, unsoiled and free of separating substances (grease, oil etc.). Subsurfaces must be free of substances containing tar as this would reduce adhesion. *FIX-O-FLEX bonding adhesive* is a suitable solvent for cleaning surfaces.

FIX-O-FLEX Primer is evenly applied on the surface with a brush or a roller. The selected *FIX-O-FLEX* adhesion and sealing compounds can be applied after the flash off time .

Please note:

FIX-O-FLEX Primer contains solvents and isocyanates. The precautionary measures and safety recommendations included in the Safety Data Sheet must be read and understood prior to starting work.

Proper and as a result successful use of our products is beyond our control. For this reason we can only guarantee the quality of our products within the framework of our Terms and Conditions of Sale and Delivery, not, however, for their successful processing. All data and information in these instructions are based on the latest state-of-the-art technology, we expressly reserve the right to make modifications or adaptations to the development. The consumption data quoted by us can only be average experience values, deviations in individual cases are possible and can therefore not be excluded.

TPH. 100908